# Advanced Wear Resistance Technology

**Engineered for Tire Recycling** 






## **POSTLE INDUSTRIES**

- → OVER 50 YEARS OF EXPERIENCE IN THE MANUFACTURE OF HARDFACING CONSUMABLES
- → CONSUMABLES DEVELOPED SPECIFICALLY FOR TIRE SHREDDING KNIVES
- + CAN CUSTOMIZE PRODUCTS TO FIT YOUR NEEDS
- + TECHNICAL EXPERTISE IN WELDING PROCEDURES AND APPLICATIONS
- + ABLE TO PROVIDE TRAINING





### **PRODUCT FEATURES**

- + EXCELLENT OPERATOR APPEAL
- + LOW SPATTER
- + EASY FEEDABILITY
- + SUPERIOR EDGE RETENTION
- + SLAG FREE
- + ABRASION AND IMPACT RESISTANT



### POSTALLOY® DURAHARD 2898 - MCG

Short-Arc	Spray-Arc				
.045" (1.2mm)		A general purpose self-hardening overlay wire with a balanced resistance to abrasion and impact. Has good metal-to-metal wear resistance and is resistant			
17-19 Volts Argon/CO2 30-35 CFH 1/2" Stickout	26-29 Volts Argon/Oxygen 40-45 CFH 5/8" Stickout	to chipping and spalling. Deposits will retain their hardness and maintain a good cutting edge up to 1100°F (595°C). For maximum impact resistance and to avoid cracking in multi-layer deposits, a preheat of 550°F (288°C) is recommended. For repeated multi-layer deposits, a preheat of 650°F (343°C) is recommended.			
1/16" (1.6mm)					
19-21 Volts	28-30 Volts	Hardness	55 – 59 Rc		
Argon/CO2	Argon/Oxygen	Non-Machinable	Must be ground		
30-35 CFH	40-45 CFH	Maximum Overlay	Unlimited with proper procedure		
3/4" Stickout	3/4" Stickout				
25 Lb. Spools, 110 Lb. Drums, 220 Lb. Drums					

#### **POSTALLOY® SUPER-EDGE**

Short-Arc	Spray-Arc	An abrasion resistant, non-cracking, high speed tool steel designed for applications			
.045" (1.2mm)		where edge retention is a primary concern. Weld deposits are martensitic with micro-			
17-19 Volts	26-29 Volts	carbides evenly dispersed throughout the deposit. These properties create a fracture resistant cutting edge even under high compressive loads. It's alloyed with molybdenum and tungsten for superior high temperature hot hardness. This property helps maintain a sharp edge under localized high heat conditions created by extreme friction.			
Argon/CO2	Argon/Oxygen				
30-35 CFH	40-45 CFH				
1/2" Stickout	5/8" Stickout	Please contact Postle Industries for proper procedures.			
1/16" (1.6mm)					
19-21 Volts	28-30 Volts	Hardness	60 – 65 Rc		
Argon/CO2	Argon/Oxygen	Non-Machinable	Must be ground		
30-35 CFH	40-45 CFH	Maximum Overlay	2 – 3 Layers		
3/4" Stickout	3/4" Stickout	,	,		
25 Lb. Spools, 110 Lb. Drums, 220 Lb. Drums					

### **POSTALLOY® ULTRA-SHRED 580**

Short-Arc	Spray-Arc	The ultimate hardfacing wire for tire shredding knives.			
.045" (1.2mm)		A non-cracking martensitic tool steel type alloy with numerous tightly packed			
17-19 Volts	26-29 Volts	carbides for excellent abrasion resistance under high impact. One-layer deposits exhibit wear characteristics that would be expected from a chromium carbide hardfacing product. The alloy properties create a resistant cutting edge even under high heat conditions created by extreme friction.			
Argon/CO2	Argon/Oxygen				
30-35 CFH	40-45 CFH				
1/2" Stickout	5/8" Stickout				
1/16" (1.6mm)					
19-21 Volts	28-30 Volts	Hardness	57 – 60 Rc		
Argon/CO2	Argon/Oxygen	Non-Machinable	Must be ground		
30-35 CFH	40-45 CFH	Maximum Overlay	Unlimited with proper procedure		
3/4" Stickout	3/4" Stickout	,			
25 Lb. Spools, 110 Lb. Drums, 220 Lb. Drums					







CLEVELAND OHIO 44142, USA +1.216.265.9000, FAX: +1.216.265.9030

NORTH AYRSHIRE, SCOTLAND KA12 8LN +44 1294 446017

www.hardfacetechnologies.com